

## Rockwool Marine Firebatts 100

### Product description

Rockwool Marine Firebatts 100 is a semi-rigid slab made of stone wool.

The product can be supplied with reinforced alu foil or glass fabric.

#### Application

Marine Firebatts 100 is primarily used as part of approved A constructions for Deck and Bulkhead.




### Technical properties

Parameter	Value	Standard
<b>Thermal conductivity</b>	$\lambda_{10} = 0,035 \text{ W/mK}$	EN 12667
<b>Nominal density</b>	100 - 115 kg/m <sup>3</sup>	-
<b>Compressive strength</b>	-	EN 826
<b>Fire classification</b>	Non-combustible Approved for A constructions	IMO A.799(19) IMO A.754(18)
<b>Max. service temp.</b>	Wool: 750°C Facing: 80°C	-
<b>Sound absorption directly mounted</b>	$\alpha_w = 0,80$ Thickness: 40 mm	$\alpha_w = 0,90$ Thickness: 60 mm
<b>Facings (on request)</b>	Reinforced alu foil White glass fabric 210 g/m <sup>2</sup> (GW200)	ISO 354 (approximated) Evaluated after ISO 11 654 IMO A.653(16) (low flame - spread)
<b>Dimensions</b>	Marine Firebatt 100: L: 1000 mm - W: 600 mm - T: 25,40,60 mm Marine Firebatt 100 w. reinf. alu: L: 1000 mm - W: 600 mm - T: 25,40,60 mm Marine Firebatt 100 GW 200: L: 1000 mm - W: 600 mm - T: 25,40,60 mm	



Rockwool A/S  
DK-2640 Hedehusene  
Tel.: +45 46 56 16 16  
Fax: +45 46 56 16 04  
E-mail: export@rockwool.dk  
Internet: www.rockwool-marine.com

Rockwool Marine & Offshore:  
Hong Kong Office  
Suite 1303, Asia Orient Tower, Town Place  
33 Lockhart Road, Wanchai, Hong Kong  
Tel: +852 2866 6180  
Fax: +852 2866 9555



Rockwool A/S reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.