

Rockwool Marine Firebatts 110

Product description

Rockwool Marine Firebatts 110 is a semi-rigid slab made of stone wool.

Application

Marine Firebatts 110 is primarily used as high temperature insulation. Furthermore the products can be used as insulation of structures where the temperature exceeds 250°C.




Technical properties

Parameter	Value	Standard
Thermal conductivity	$\lambda_{10} = 0,035 \text{ W/mK}$ $\lambda_{100} = 0,045 \text{ W/mK}$ $\lambda_{300} = 0,084 \text{ W/mK}$	EN 12667
Nominal density	110 kg/m ³	-
Compressive strength	-	EN 826
Fire classification	Non-combustible	IMO A.799(19)
Max. service temp.	Wool: 750°C	-
Sound absorption directly mounted	-	ISO 354 (approximated) Evaluated after ISO 11 654
Facings	-	IMO A.653(16) (low flame - spread)
Dimensions	Marine Firebatts 110: L: 1000 mm - W: 600 mm - T: 25,50 mm	



Rockwool A/S
 DK-2640 Hedehusene
 Tel.: +45 46 56 16 16
 Fax: +45 46 56 16 04
 E-mail: export@rockwool.dk
 Internet: www.rockwool-marine.com

Rockwool Marine & Offshore:
 Hong Kong Office
 Suite 1303, Asia Orient Tower, Town Place
 33 Lockhart Road, Wanchai, Hong Kong
 Tel: +852 2866 6180
 Fax: +852 2866 9555



Rockwool A/S reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.